

URS 5160

Revised 9/27/01

NON-MDA LOW MOISTURE SENSITIVE POLYURETHANE CASTING SYSTEM

60 SHORE A

DESCRIPTION

URS 5160 is an amber, two component, NON-MDA, polyether based urethane casting system designed for low moisture sensitivity. **URS 5160's** unique handling characteristics allow for castings to be made on typically difficult moisture absorbing surfaces, wood-plasters-ceramics, without interacted exchange. **URS 5160** also sets and cures at room temperature, ideal for proto mold making, vibration damping parts, bumper pads, stripers, etc.

FEATURES

NON-MDA
Extremely Low Shrinkage
Low Moisture Sensitivity
Room Temperature Processing
High Impact Strength
No MOCA or TDI
Hand or Machine Processing

LIQUID

<u>PROPERTIES</u>	<u>AMN 1040B</u>	<u>ISO 490A</u>	<u>MIXED</u>
Appearance	Lt. Brown Liquid	Clear Liquid	Lt. Brown Liquid
Viscosity (cps)	200 - 700 (77F)	4,000-6,000 (77F)	4,000-5,000 (77F)
Density (lbs/gal)	8.40 - 8.55	9.80 – 10.00	9.65 – 9.90

PHYSICAL PROPERTIES

Hardness, Shore A	60
Tensile Strength, Ultimate, psi	1250
Elongation, %	475
Tear Strength PLI	165

LINEAR SHRINKAGE

D-2566	.0005 In/In
1.125" Deep	

URS 5160 Continued:

PROCESSING PARAMETERS

Process AMN 1040B at 65 to 100 degrees F.

Melt Isocyanate 490A if frozen at 100 degrees F., otherwise use at 60 - 85 degrees F.

Mold Temperature: 60 to 100 degrees F.

Mix Ratio: 10 parts AMN 1040B to 100 parts Isocyanate 490A by weight.

Pot Life: (200g mass) (77 F) 10 to 20 minutes.

Demold: 1 - 2 hours or 30 - 45 minutes with maximum process and moderate temperatures.

Post Cure: 16 - 24 hours @ 77 degrees F.

STORAGE

Systems should be stored unopened in air tight containers at 60 - 90 degrees F. Partially emptied containers should be swept free of atmospheric moisture with dry nitrogen before sealing.

HANDLING PRECAUTIONS

For complete and updated health and safety information, read the MATERIAL SAFETY DATA SHEETS. Do not handle or use until the MATERIAL SAFETY DATA SHEETS have been read and understood.